



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C08K 11/00, C08J 3/22	A1	(11) International Publication Number: WO 98/56854 (43) International Publication Date: 17 December 1998 (17.12.98)
(21) International Application Number: PCT/US98/11959 (22) International Filing Date: 4 June 1998 (04.06.98) (30) Priority Data: 60/049.077 9 June 1997 (09.06.97) US 60/069.935 17 December 1997 (17.12.97) US 60/079.225 24 March 1998 (24.03.98) US (71) Applicant: NANOMATERIALS RESEARCH CORPORATION [US/US]: 2849 East Elvira Road, Tucson, AZ 85706 (US). (72) Inventors: YADAV, Tapesht; 4101 Via del Cuculin, Tucson, AZ 85718 (US). KOSTELECKY, Clayton; 2424 9th Avenue #1101, Longmont, CO 80503 (US). FRANKE, Evan; 2424 9th Avenue #3101, Longmont, CO 80503 (US). MIREMADI, Bijan; Apartment 8, 1447 Kimbark Street, Longmont, CO 80501 (US). AU, Ming; 250 N. Arcadia Avenue #616, Tucson, AZ 85711 (US). (74) Agent: PASTERNAK, Sam; Choate, Hall & Stewart, Exchange Place, 53 State Street, Boston, MA 02109 (US).		(81) Designated States: CA, JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: NANOSTRUCTURED FILLERS AND CARRIERS (57) Abstract <p>A nanocomposite structure comprising a nanostructured filler or carrier intimately mixed with a matrix, and methods of making such a structure. The nanostructured filler has a domain size sufficiently small to alter an electrical, magnetic, optical, electrochemical chemical, thermal, biomedical, or tribological property of either filler or composite by at least 20 %.</p> <div data-bbox="1006 1113 1250 1386"></div> <div data-bbox="1169 1827 1315 1953">1-16 21</div>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Nanostructured Fillers and Carriers

This application claims benefit and priority of U.S. Provisional Patent Applications 60/049,077, filed June 5, 1997; 60/069,935, filed December 17, 1997; and 60/079,225, filed March 24, 1998.

Field of the Invention

This invention relates to the use of nanoscale powders as a component of novel composites and devices. By incorporating powders having dimensions less than a characteristic domain size into polymeric and other matrices, nanocomposites with unique properties can be produced.

Background of the Invention

A very wide variety of pure phase materials such as polymers are now readily available at low cost. However, low cost pure phase materials are somewhat limited in the achievable ranges of a number of properties, including, for example, electrical conductivity, magnetic permeability, dielectric constant, and thermal conductivity. In order to circumvent these limitations, it has become common to form composites, in which a matrix is blended with a filler material with desirable properties. Examples of these types of composites include the carbon black and ferrite mixed polymers that are used in toners, tires, electrical devices, and magnetic tapes.

The number of suitable filler materials for composites is large, but still limited. In particular, difficulties in fabrication of such composites often arise due to issues of interface stability between the filler and the matrix, and because of the difficulty of orienting and homogenizing filler material in the matrix. Some desirable properties of the matrix (e.g., rheology) may also be lost when certain fillers are added, particularly at the high loads required by many applications. The availability of new filler materials, particularly materials with novel properties, would significantly expand the scope of manufacturable composites of this type.

Summary of the Invention

In one aspect, the invention comprises a nanostructured filler, intimately mixed with a matrix to form a nanostructured composite. At least one of the nanostructured filler and the nanostructured composite has a desired material property which differs by at least 20% from the same material property for a micron-scale filler or a micron-scale composite, respectively. The desired material property is selected from the group consisting of refractive index, transparency to light, reflection characteristics, resistivity, permittivity, permeability, coercivity, B-H product, magnetic hysteresis, breakdown voltage, skin depth, curie temperature, dissipation factor, work function, band gap, electromagnetic shielding effectiveness, radiation hardness, chemical reactivity, thermal conductivity, temperature coefficient of an electrical property, voltage coefficient of an electrical property, thermal shock resistance, biocompatibility and wear rate.

The nanostructured filler may comprise one or more elements selected from the s, p, d, and f groups of the periodic table, or it may comprise a compound of one or more such elements with one or more suitable anions, such as aluminum, antimony, boron, bromine, carbon, chlorine, fluorine, germanium, hydrogen, indium, iodine, nickel, nitrogen, oxygen, phosphorus, selenium, silicon, sulfur, or tellurium. The matrix may be a polymer (*e.g.*, poly(methyl methacrylate), poly(vinyl alcohol), polycarbonate, polyalkene, or polyarylether), a ceramic (*e.g.*, zinc oxide, indium-tin oxide, hafnium carbide, or ferrite), or a metal (*e.g.*, copper, tin, zinc, or iron). Loadings of the nanofiller may be as high as 95%, although loadings of 80% or less are preferred. The invention also comprises devices which incorporate the nanofiller (*e.g.*, electrical, magnetic, optical, biomedical, and electrochemical devices).

Another aspect of the invention comprises a method of producing a composite, comprising blending a nanoscale filler with a matrix to form a nanostructured composite. Either the nanostructured filler or the composite itself differs substantially in a desired material property from a micron-scale filler or composite, respectively. The desired material property is selected from the group consisting of refractive index, transparency to light, reflection characteristics, resistivity, permittivity, permeability, coercivity, B-H product, magnetic hysteresis, breakdown voltage, skin depth, curie temperature, dissipation factor, work function, band gap, electromagnetic

shielding effectiveness, radiation hardness, chemical reactivity, thermal conductivity, temperature coefficient of an electrical property, voltage coefficient of an electrical property, thermal shock resistance, biocompatibility, and wear rate. The loading of the filler does not exceed 95 volume percent, and loadings of 80 volume percent or less are preferred.

The composite may be formed by mixing a precursor of the matrix material with the nanofiller, and then processing the precursor to form a desired matrix material. For example, the nanofiller may be mixed with a monomer, which is then polymerized to form a polymer matrix composite. In another embodiment, the nanofiller may be mixed with a matrix powder composition and compacted to form a solid composite. In yet another embodiment, the matrix composition may be dissolved in a solvent and mixed with the nanofiller, and then the solvent may be removed to form a solid composite. In still another embodiment, the matrix may be a liquid or have liquid like properties.

Many nanofiller compositions are encompassed within the scope of the invention, including nanofillers comprising one or more elements selected from the group consisting of actinium, aluminum, arsenic, barium, beryllium, bismuth, cadmium, calcium, cerium, cesium, cobalt, copper, dysprosium, erbium, europium, gadolinium, gallium, gold, hafnium, hydrogen, indium, iridium, iron, lanthanum, lithium, magnesium, manganese, mendelevium, mercury, molybdenum, neodymium, neptunium, nickel, niobium, osmium, palladium, platinum, potassium, praseodymium, promethium, protactinium, rhenium, rubidium, scandium, silver, sodium, strontium, tantalum, terbium, thallium, thorium, tin, titanium, tungsten, vanadium, ytterbium, yttrium, zinc, and zirconium.

"Domain size," as that term is used herein, refers to the minimum dimension of a particular material morphology. In the case of powders, the domain size is the grain size. In the case of whiskers and fibers, the domain size is the diameter. In the case of plates and films, the domain size is the thickness.

As used herein, a "nanostructured" powder is one having a domain size of less than 100 nm. or alternatively, having a domain size sufficiently small that a selected material property is substantially different from that of a micron-scale powder, due to size confinement effects (*e.g.*, the property may differ by 20% or more from the

analogous property of the micron-scale material). Nanostructured powders often advantageously have sizes as small as 50 nm, 30 nm, or even smaller. Nanostructured powders may also be referred to as "nanopowders," or "nanofillers." A nanostructured composite is a composite comprising a nanostructured phase dispersed in a matrix.

As it is used herein, the term "agglomerated" describes a powder in which at least some individual particles of the powder adhere to neighboring particles, primarily by electrostatic forces, and "aggregated" describes a powder in which at least some individual particles are chemically bonded to neighboring particles.

As it is used herein, the term "device" includes mechanical, electrical, electronic, biomedical, and other apparatuses and structures which may be manufactured for a wide variety of purposes.

Brief Description of the Drawing

The invention is described with reference to the several figures of the drawing, in which.

Figure 1 is a diagram of a nanostructured filler coated with a polymer;

Figure 2 portrays an X-ray diffraction (XRD) spectrum for the stoichiometric indium tin oxide powder of Example 1;

Figure 3 is a scanning electron microscope (SEM) micrograph of the stoichiometric indium tin oxide powder of Example 1; and

Figure 4 is a diagram of the nanostructured varistor of Example 5.

Detailed Description

Prior art filler materials for polymeric composites are usually powders with an average dimension in the range of 10-100 μm . Thus, each filler particle typically has on the order of 10^{15} - 10^{18} atoms. In contrast, the typical polymer chain has on the order of 10^3 - 10^9 atoms. While the art of precision manufacturing of polymers at molecular levels is well-developed, the knowledge of precision manufacturing of filler materials at molecular levels has remained largely unexplored.

The number of atoms in the filler particles of the invention (hereinafter called

“nanostructured filler” or “nanofiller”) is on the order of or significantly less than the number of atoms in the polymer molecules, *e.g.*, 10^2 - 10^{10} . Thus, the filler particles are comparable in size or smaller than the polymer molecules, and therefore can be dispersed with orders of magnitude higher number density. Further, the fillers may have a dimension less than or equal to the critical domain sizes that determine the characteristic properties of the bulk composition; thus, the fillers may have significantly different physical properties from larger particles of the same composition. This in turn may yield markedly different properties in composites using nanofillers as compared to the typical properties of conventional polymer composites.

These nanostructured filler materials may also have utility in the manufacture of other types of composites, such as ceramic- or metal-matrix composites. Again, the changes in the physical properties of the filler particles due to their increased surface area and constrained domain sizes can yield changes in the achievable properties of composites.

The nanofillers of the invention can be inorganic, organic, or metallic, and may be in the form of powders, whiskers, fibers, plates or films. The fillers represent an additive to the overall composite composition, and may be used at loadings of up to 95% by volume. The fillers may have connectivity in 0, 1, 2, or 3 dimensions. Fillers may be produced by a variety of methods, such as those described in U.S. Patent Nos. 5,486,675; 5,447,708; 5,407,458; 5,219,804; 5,194,128; and 5,064,464. Particularly preferred methods of making nanostructured fillers are described in U.S. Patent Application 09/046,465, by Bickmore, *et al.*, filed March 23, 1998, and 08/706,819, by Pirzada, *et al.*, filed September 3, 1996, both of which are incorporated herein by reference.

A wide variety of nanofiller compositions are possible. Some exemplary compositions include metals (*e.g.*, Cu, Ag, Ni, Fe, Al, Pd, and Ti), oxide ceramics (*e.g.*, TiO_2 , TiO_{2-x} , BaFe_2O_4 , dielectric compositions, ferrites, and manganites), carbide ceramics (*e.g.*, SiC, BC, TiC, WC, WC_{1-x}), nitride ceramics (*e.g.*, Si_3N_4 , TiN, VN, AlN, and Mo_2N), hydroxides (*e.g.*, aluminum hydroxide, calcium hydroxide, and barium hydroxide), borides (*e.g.*, AlB_2 and TiB_2), phosphides (*e.g.*, NiP and VP), sulfides (*e.g.*, molybdenum sulfide, titanium sulfide, and tungsten sulfide), silicides

(e.g., MoSi_2), chalcogenides (e.g., Bi_2Te_3 , Bi_2Se_3), and combinations of these.

The fillers are intimately mixed with a matrix material, which is preferably polymeric, but may also be ceramic, metallic, or a combination of the above. The matrix may be chosen for properties such as ease of processability, low cost,
5 environmental benignity, commercial availability, and compatibility with the desired filler. The fillers are preferably mixed homogeneously into the matrix, but may also be mixed heterogeneously if desired, for example to obtain a composite having a gradient of some property. Mixing techniques for incorporating powders into fluids and for mixing different powders are well known in the art, and include mechanical,
10 thermal, electrical, magnetic, and chemical momentum transfer techniques, as well as combinations of the above.

The viscosity, surface tension, and density of a liquid matrix material can be varied for mixing purposes, the preferred values being those that favor ease of mixing and that reduce energy needed to mix without introducing any undesirable
15 contamination. One method of mixing is to dissolve the matrix in a solvent which does not adversely affect the properties of the matrix or the filler and which can be easily removed and recovered. Another method is to melt the matrix, incorporate the filler, and cool the mixture to yield a solid composite with the desired properties. Yet another method is to synthesize the matrix *in-situ* with the filler present. For
20 example, the nanofiller can be mixed with a liquid monomer, which can then be polymerized to form the composite. In this method, the filler may be used as a catalyst or co-catalyst for polymerization. The mixing may also be accomplished in the solid state, for example by mixing a powdered matrix composition with the filler, and then compacting the mixture to form a solid composite.

25 Mixing can be assisted using various secondary species such as dispersants, binders, modifiers, detergents, and additives. Secondary species may also be added to enhance one or more of the properties of the filler-matrix composite.

Mixing can also be assisted by pre-coating the nanofiller with a thin layer of the matrix composition or with a phase that is compatible with the matrix
30 composition. Such a coated nanoparticle is illustrated in **Figure 1**, which shows a spherical nanoparticle 6 and a coating 8. In one embodiment, when embedding nanofillers in a polymer matrix, it may be desirable to coat the filler particles with a

related monomer. When mixing nanofillers into a ceramic matrix, pre-coating can be done by forming a ceramic layer around the nanoscale filler particle during or after the synthesis of the nanoscale filler, by methods such as partial oxidation, nitridation, carborization, or boronation. In these methods, the nanostructured filler is exposed to a small concentration of a precursor that reacts with the surface of the filler to form a ceramic coating. For example, a particle may be exposed to oxygen in order to create an oxide coating, to ammonia in order to create a nitride coating, to borane to create a boride coating, or to methane to create a carbide coating. It is important that the amount of precursor be small, to prevent thermal runaway and consequent conversion of the nanostructured filler into a ceramic particle.

In case of polymer matrix, the filler can be coated with a polymer or a monomer by numerous methods, for example, surface coating *in-situ*, spray drying a dispersion of filler and polymer solution, co-polymerization on the filler surface, and melt spinning followed by milling. A preferred method is surface coating *in-situ*. In this process, the filler is first suspended in demineralized water (or another solvent) and the suspension's pH is measured. The pH is then adjusted and stabilized with small addition of acid (*e.g.*, acetic acid or dilute nitric acid) or base (*e.g.*, ammonium hydroxide or dilute sodium hydroxide). The pH adjustment produces a charged state on the surface of the filler. Once a desired pH has been achieved, a coating material (for example, a polymer or other appropriate precursor) with opposite charge is introduced into the solvent. This step results in coupling of the coating material around the nanoscale filler and formation of a coating layer around the nanoscale filler. Once the layer has formed, the filler is removed from the solvent by drying, filtration, centrifugation, or any other method appropriate for solid-liquid separation. This technique of coating a filler with another material using surface charge can be used for a variety of organic and inorganic compositions.

When a solvent is used to apply a coating as in the *in-situ* surface coating method described above, the matrix may also be dissolved in the solvent before or during coating, and the final composite formed by removing the solvent.

A very wide range of material properties can be engineered by the practice of the invention. For example, electrical, magnetic, optical, electrochemical, chemical, thermal, biomedical, and tribological properties can be varied over a wider range than

is possible using prior art micron-scale composites.

Nanostructured fillers can be used to lower or raise the effective resistivity, effective permittivity, and effective permeability of a polymer or ceramic matrix. While these effects are present at lower loadings, they are expected to be most pronounced for filler loadings at or above the percolation limit of the filler in the matrix (*i.e.*, at loadings sufficiently high that electrical continuity exists between the filler particles). Other electrical properties which may be engineered include breakdown voltage, skin depth, curie temperature, temperature coefficient of electrical property, voltage coefficient of electrical property, dissipation factor, work function, band gap, electromagnetic shielding effectiveness and degree of radiation hardness. Nanostructured fillers can also be used to engineer magnetic properties such as the coercivity, B-H product, hysteresis, and shape of the B-H curve of a matrix.

An important characteristic of optical material is its refractive index and its transmission and reflective characteristics. Nanostructured fillers may be used to produce composites with refractive index engineered for a particular application. Gradient lenses may be produced using nanostructured materials. Gradient lenses produced from nanostructured composites may reduce or eliminate the need for polishing lenses. The use of nanostructured fillers may also help filter specific wavelengths. Furthermore, a key advantage of nanostructured fillers in optical applications is expected to be their enhanced transparency because the domain size of nanostructured fillers ranges from about the same as to more than an order of magnitude less than visible wavelengths of light.

The high surface area and small grain size of nanofilled composites make them excellent candidates for chemical and electrochemical applications. When used to form electrodes for electrochemical devices, these materials are expected to significantly improve performance, for example by increasing power density in batteries and reducing minimum operating temperatures for sensors. (An example of the latter effect can be found in copending and commonly assigned U.S. Application 08/739,257, "Nanostructured Ion Conducting Solid Electrolytes," by Yadav, *et al.*). Nanostructured fillers are also expected to modify the chemical properties of composites. These fillers are catalytically more active, and provide more interface

area for interacting with diffusive species. Such fillers may, for example, modify chemical stability and mobility of diffusing gases. Furthermore, nanostructured fillers may enhance the chemical properties of propellants and fuels.

5 Many nanostructured fillers have a domain size comparable to the typical mean free path of phonons at moderate temperatures. It is thus anticipated that these fillers may have dramatic effects on the thermal conductivity and thermal shock resistance of matrices into which they are incorporated.

10 Nanostructured fillers - in coated and uncoated form - and nanofilled composites are also expected to have significant value in biomedical applications for both humans and animals. For example, the small size of nanostructured fillers may make them readily transportable through pores and capillaries. This suggests that the fillers may be of use in developing novel time-release drugs and methods of administration and delivery of drugs, markers, and medical materials. A polymer coating can be utilized either to make water-insoluble fillers into a form that is water
15 soluble, or to make water-soluble fillers into a form that is water insoluble. A polymer coating on the filler may also be utilized as a means to time drug-release from a nanoparticle. A polymer coating may further be used to enable selective filtering, transfer, capture, and removal of species and molecules from blood into the nanoparticle.

20 A nanoparticulate filler for biomedical operations might be a carrier or support for a drug of interest, participate in the drug's functioning, or might even be the drug itself. Possible administration routes include oral, topical, and injection routes. Nanoparticulates and nanocomposites may also have utility as markers or as carriers for markers. Their unique properties, including high mobility and unusual physical
25 properties, make them particularly well-adapted for such tasks.

In some examples of biomedical functions, magnetic nanoparticles such as ferrites may be utilized to carry drugs to a region of interest, where the particles may then be concentrated using a magnetic field. Photocatalytic nanoparticles can be utilized to carry drugs to region of interest and then photoactivated. Thermally
30 sensitive nanoparticles can similarly be utilized to transport drugs or markers or species of interest and then thermally activated in the region of interest. Radioactive nanoparticulate fillers may have utility for chemotherapy. Nanoparticles suitably

doped with genetic and culture material may be utilized in similar way to deliver therapy in target areas. Nanocomposites may be used to assist in concentrating the particle and then providing the therapeutic action. To illustrate, magnetic and photocatalytic nanoparticles may be formed into a composite, administered to a patient, concentrated in area of interest using magnetic field, and finally activated using photons in the concentrated area. As markers, nanoparticulate fillers - coated or uncoated - may be used for diagnosis of medical conditions. For example, fillers may be concentrated in a region of the body where they may be viewed by magnetic resonance imaging or other techniques. In all of these applications, the possibility exists that nanoparticulates can be released into the body in a controlled fashion over a long time period, by implanting a nanocomposite material having a bioabsorbable matrix, which slowly dissolves in the body and releases its embedded filler.

As implants, nanostructured fillers and composites are expected to lower wear rate and thereby enhance patient acceptance of surgical procedures. Nanostructured fillers may also be more desirable than micron-scale fillers, because the possibility exists that their domain size may be reduced to low enough levels that they can easily be removed by normal kidney action without the development of stones or other adverse side effects. While nanoparticulates may be removed naturally through kidney and other organs, they may also be filtered or removed externally through membranes or otherwise removed directly from blood or tissue. Carrier nanoparticulates may be reactivated externally through membranes and reused: for example, nutrient carriers may be removed from the bloodstream, reloaded with more nutrients, and returned to carry the nutrients to tissue. The reverse process may also be feasible, wherein carriers accumulate waste products in the body, which are removed externally, returning the carriers to the bloodstream to accumulate more waste products.

Examples

Example 1 - Indium Tin Oxide fillers in PMMA

A stoichiometric (90 wt% In_2O_3 in SnO_2) indium tin oxide (ITO) nanopowder was produced using the methods of copending patent application 09/046,465. 50 g of indium shot was placed in 300 ml of glacial acetic acid and 10 ml of nitric acid. The

combination, in a 1000 ml Erlenmeyer flask, was heated to reflux while stirring for 24 hours. At this point, 50 ml of HNO₃ was added, and the mixture was heated and stirred overnight. The solution so produced was clear, with all of the indium metal dissolved into the solution, and had a total final volume of 318 ml. An equal volume
5 (318 mL) of 1-octanol was added to the solution along with 600 mL ethyl alcohol in a 1000 mL HDPE bottle, and the resulting mixture was vigorously shaken. 11.25 ml of tetrabutyltin was then stirred into the solution to produce a clear indium/tin emulsion. When the resulting emulsion was burned in air, it produced a brilliant violet flame. A yellow nanopowder residue was collected from the flamed emulsion. The
10 nanopowder surface area was 13.5 m²/gm. and x-ray diffractometer mean grain size was 60 nm.

Figure 2 shows the measured X-ray diffraction (XRD) spectrum for the powder, and **Figure 3** shows a scanning electron microscope (SEM) image of the powder. These data show that the powder was of nanometer scale.

15 The nanostructured powder was then mixed with poly(methyl methacrylate) (PMMA) in a ratio of 20 vol% powder to 80 vol% PMMA. The powder and the polymer were mixed using a mortar and pestle, and then separated into three parts, each of which was pressed into a pellet. The pellets were pressed by using a Carver hydraulic press, pressing the mixture into a 1/4 inch diameter die using a 1500 pound
20 load for one minute.

After removal from the die, the physical dimensions of the pellets were measured, and the pellets were electroded with silver screen printing paste (Electro Sciences Laboratory 9912-F).

Pellet resistances were measured at 1 volt using a Megohmmeter / IR tester
25 1865 from QuadTech with a QuadTech component test fixture. The volume resistivity was calculated for each pellet using the standard relation,

$$\rho = R \left(\frac{A}{t} \right) \quad (1)$$

where ρ represents volume resistivity in ohm-cm, R represents the measured resistance in ohms, A represents the area of the electroded surface of the pellet in cm²,
30 and t represents the thickness of the pellet in cm. The average volume resistivity of

the stoichiometric ITO composite pellets was found to be 1.75×10^4 ohm-cm.

Another quantity of ITO nanopowder was produced as described above, and was reduced by passing 2 SCFM of forming gas (5% hydrogen in nitrogen) over the powder while ramping temperature from 25°C to 250°C at 5 °C/min. The powder was held at 250°C for 3 hours, and then cooled back to room temperature. The XRD spectrum of the resulting powder indicated that the stoichiometry of the reduced powder was $\text{In}_{18}\text{SnO}_{29-x}$, with x greater than 0 and less than 29.

The reduced ITO nanopowder was combined with PMMA in a 20:80 volume ratio and formed into pellets as described above. The pellets were electroded as described, and their resistivity was measured. The average resistivity for the reduced ITO composite pellets was found to be 1.09×10^4 ohm-cm.

For comparison, micron scale ITO was purchased from Alfa Aesar (catalog number 36348), and was formed into pellets with PMMA and electroded as described above. Again, the volume fraction of ITO was 20%. The average measured resistivity of the micron scale ITO composite pellets was found to be 8.26×10^8 ohm-cm, representing a difference of more than four orders of magnitude from the nanoscale composite pellets. It was thus established that composites incorporating nanoscale fillers can have unique properties not achievable by prior art techniques.

Example 2 - Hafnium Carbide fillers in PMMA

Nanoscale hafnium carbide fillers were prepared as described in copending U.S. Patent Applications 08/706,819 and 08/707,341. The nanopowder surface area was 53.5 m²/gm, and mean grain size was 16 nm. Micron scale hafnium carbide powder was purchased from Cerac (catalog number H-1004) for comparison.

Composite pellets were produced as described in Example 1, by mixing filler and polymer with a mortar and pestle and pressing in a hydraulic press. Pellets were produced containing either nanoscale or micron scale powder at three loadings: 20 vol% powder, 50 vol% powder, and 80 vol% powder. The pellets were electroded as described above, and their resistivities were measured. (Because of the high resistances at the 20% loading, these pellets' resistivities were measured at 100V. The other pellets were measured at 1V, as described in Example 1).

Results of these resistivity measurements are summarized in Table 1. As can

be seen, the resistivity of the pellets differed substantially between the nanoscale and micron scale powders. The composites incorporating nanoscale powder had a somewhat decreased resistivity compared to the micron scale powder at 20% loading, but had a dramatically increased resistivity compared to the micron scale powder at 50% and 80% loading.

Volume % filler	Resistivity of nanoscale powder composite (ohm-cm)	Resistivity of micron scale powder composite (ohm-cm)
20	5.54×10^{12}	7.33×10^{13}
50	7.54×10^9	2.13×10^4
80	3.44×10^9	1.14×10^4

Table 1

Example 3 - Copper fillers in PMMA and PVA

Nanoscale copper powders were produced as described in U.S. Patent Applications 08/706,819 and 08/707,341. The nanopowder surface area was 28.1 m²/gm, and mean grain size was 22 nm. Micron scale copper powder was purchased from Aldrich (catalog number 32645-3) for comparison.

The nanoscale and micron scale copper powders were each mixed at a loading of 20 vol% copper to 80 vol% PMMA and formed into pellets as described above. In addition, pellets having a loading of 15 vol% copper in poly(vinyl alcohol) (PVA) were produced by the same method. The pellets were electroded and resistivities measured at 1 volt as described in Example 1. Results are shown in Table 2.

Additive	Polymer	Volume % filler	Volume Resistivity (ohm-cm)
nanoscale copper	PMMA	20	5.68×10^{10}
nanoscale copper	PVA	15	4.59×10^5
micron scale copper	PMMA	20	4.19×10^{12}

Table 2

It can be seen from **Table 2** that the resistivity of the nanoscale copper powder / PMMA composite was substantially reduced compared to the micron scale copper powder / PMMA composite at the same loading, and that the resistivity of the nanoscale copper powder / PVA composite was lower still by five orders of magnitude.

Example 4 - Preparation of Polymer-coated Nanostructured Filler

The stoichiometric (90 wt% In_2O_3 in SnO_2) indium tin oxide (ITO) nanopowder of Example 1 was coated with a polymer as follows.

200 milligrams of ITO nanopowders with specific surface area of $53 \text{ m}^2/\text{gm}$ were added to 200 ml of demineralized water. The pH of the suspension was adjusted to 8.45 using ammonium hydroxide. In another container, 200 milligrams of poly(methyl methacrylate) (PMMA) was dissolved in 200 ml of ethanol. The PMMA solution was warmed to 100°C while being stirred. The ITO suspension was added to the PMMA solution and the stirring and temperature of 100°C was maintained till the solution reduced to a volume of 200 ml. The solution was then cooled to room temperature to a very homogenous solution with very light clear-milky color. The optical clarity confirmed that the powders are still nanostructured. The powder was dried in oven at 120°C and its weight was measured to be 400 milligrams. The increase in weight, uniformity of morphology and the optical clarity confirmed that the nanopowders were coated with PMMA polymer.

The electrochemical properties of polymer coated nanopowders were different than the as-produced nanopowders. The as-produced nanopowder when suspended in demineralized water yielded a pH of 3.4, while the polymer coated nanopowders had a pH of 7.51.

Example 5 - Preparation of Electrical Device Using Nanostructured Fillers

A complex oxide nanoscale filler having the following composition was prepared: Bi_2O_3 (48.8 wt%), NiO (24.4 wt%), CoO (12.2 wt%), Cr_2O_3 (2.4 wt%), MnO (12.2 wt%), and Al_2O_3 (<0.02 wt%). The complex oxide filler was prepared from the corresponding nitrates of the same cation. The nitrates of each constituent were added to 200 mL of deionized water while constantly stirring. Hydroxides were

precipitated with the addition of 50 drops of 28-30% NH_4OH . The solution was filtered in a large buchner funnel and washed with deionized water and then with ethyl alcohol. The powder was dried in an oven at 80°C for 30 minutes. The dried powder was ground using a mortar and pestle. A heat treatment schedule consisting of a $15^\circ\text{C}/\text{min}$ ramp to 350°C with a 30 minute dwell was used to calcine the ground powder.

The nanofiller was then incorporated at a loading of 4% into a zinc oxide ceramic matrix. The composite was prepared by mechanically mixing the doped oxide nanofiller powder with zinc oxide powder, incorporating the mixture into a slurry, and screen printing the slurry (further described below). For comparison, devices were made using both a nanoscale matrix powder produced by the methods of copending and commonly assigned U.S. Application 08/706,819, and using a micron scale matrix powder purchased from Chemcorp. The fillers and the matrix powders were mixed mechanically using a mortar and pestle.

Using the filler-added micron scale powder, a paste was prepared by mixing 4.0 g of powder with 2.1 g of a commercial screen printing vehicle purchased from Electro Science Laboratories (ESL vehicle 400). The doped nanoscale powder paste was made using 3.5 g powder and 3.0 g ESL vehicle 400. Each paste was mixed using a glass stir rod. Silver-palladium was used as a conducting electrode material. A screen with a rectangular array pattern was used to print each paste on an alumina substrate. First a layer of silver-palladium powder (the lower electrode) was screen printed on the substrate and dried on a hot plate. Then the ceramic filled powder was deposited, also by screen printing. Four print-dry cycles were used to minimize the possibility of pinhole defects in the varistor. Finally, the upper electrode was deposited.

The electrode/composite/electrode varistor was formed as three diagonally offset overlapping squares, as illustrated in **Figure 4**. The effective nanostructured-filler based composite area in the device due to the offset of the electrodes was 0.036 in² (0.2315 cm²). The green thick films were co-fired at 900°C for 60 minutes. The screen printed specimen is shown in **Figure 4**, where light squares **10** represent the silver-palladium electrodes, and dark square **12** represents the composite layer.

Silver leads were attached to the electrodes using silver epoxy. The epoxy

was cured by heating at a 50 °C/min ramp rate to 600°C and then cooling to room temperature at a rate of 50 °C/min. The TestPoint™ computer software, in conjunction with a Keithley® current source, was used to obtain a current-voltage curve for each of the varistors.

5 The electrode/micron scale matrix composite/electrode based varistor device had a total thickness of 29-33 microns and a composite layer thickness of 19 microns. The electrode/nanoscale matrix composite/electrode based varistor device had a total thickness of 28-29 microns and a composite layer thickness of 16 microns. Examination of current-voltage response curves for both varistors showed that the
10 nanostructured matrix varistor had an inflection voltage of about 2 volts, while the inflection voltage of the micron scale matrix varistor had an inflection voltage of about 36 volts. Fitting the current-voltage response curves to the standard varistor power-law equation

$$I = nV^\alpha \quad (2)$$

15 yielded values of voltage parameter α of 2.4 for the micron-scale matrix device, and 37.7 for the nanoscale matrix device. Thus, the nonlinearity of the device was shown to increase dramatically when the nanoscale matrix powder was employed.

Example 6 - Thermal battery electrode using a nanostructured filler

20 Thermal batteries are primary batteries ideally suited for military ordinance, projectiles, mines, decoys, torpedoes, and space exploration systems, where they are used as highly reliable energy sources with high power density and extremely long shelf life. Thermal batteries have previously been manufactured using techniques that place inherent limits on the minimum thickness obtainable while ensuring adequate
25 mechanical strength. This in turn has slowed miniaturization efforts and has limited achievable power densities, activation characteristics, safety, and other important performance characteristics. Nanocomposites help overcome this problem, as shown in the following example.

™ "Test Point" is a trademark of Keithley Scientific Instruments, Inc.

® "Keithley" is a registered trademark of Keithley Scientific Instruments, Inc.

Three grams of raw FeS_2 powder was mixed and milled with a group of hard steel balls in a high energy ball mill for 30 hours. The grain size of produced powder was 25 nm. BET analysis showed the surface area of the nanopowder to be 6.61 m^2/gm . The TEM images confirmed that the ball milled FeS_2 powder consists of the fine particles with the round shape, similar thickness and homogenous size. The cathode comprised FeS_2 nanopowders (68%), eutectic $\text{LiCl}\cdot\text{KCl}$ (30%) and SiO_2 (2%) (from Aldrich Chemical with 99% purity). The eutectic salts enhanced the diffusion of Li ions and acted as a binder. Adding silicon oxide particles was expected to immobilize the $\text{LiCl}\cdot\text{KCl}$ salt during melting. For comparison, the cathode pellets were prepared from nanostructured and micron scale FeS_2 powders separately.

To improve electrochemical efficiencies and increase the melting point of anode, we chose micron scale Li 44%-Si 56% alloy with 99.5% purity (acquired from Cyprus Foote Mineral) as the anode material in this work. A eutectic salt, LiCl 45%- KCl 55% (from Aldrich Chemical with 99% purity), was selected as electrolyte. The salt was dried at 90°C and fused at 500°C . To strengthen the pellets and prevent flowing out of electrolyte when it melted, 35% MgO (Aldrich Chemical, 99% purity) powder was added and mixed homogeneously with the eutectic salt powder.

The pellets of anode electrodes were prepared by a cold press process. A hard steel die with a 20 mm internal diameter was used to make the thin disk pellets. 0.314 grams of Li 44% - Si 56% alloy powder (with 76-422 mesh particle size) was pressed under 6000 psi static pressure to form a pellet. The thickness and density of the pellets so obtained was determined to be 0.84 mm and 1.25 g/cm^2 , respectively. Electrolyte pellets were produced using 0.55 grams of blended electrolyte powder under 4000 psi static pressure. The thickness and density of the pellets obtained were 0.84 mm and 2.08 g/cm^2 respectively. The cathode pellet was prepared using 0.91 grams of mixed micron scale FeS_2 - $\text{LiCl}\cdot\text{KCl}$ - SiO_2 powder pressed under 4000 psi static pressure. The thickness and density of the pellets obtained were 0.86 mm and 3.37 g/cm^2 , respectively.

A computerized SOLARTRON® 1287 electrochemical interface and a 1260 Gain/Phase Analyzer were employed to provide constant current and to monitor

® "Solartron" is a registered trademark of the Solartron Electronic Group, Ltd.

variation in potential between anode and cathode of cells during the discharging. The cutoff potential of discharge was set at 0.8 volt. The thermal battery with the nanocomposite cathode provided 1A constant current for 246 seconds, until the potential fell to 0.8 volt. It was observed that the power density of the nanostructured single cell thermal battery was 100% higher than that achievable with micron sized materials. Thus, nanoscale fillers can help enhance the electrochemical performance of such a device.

Example 7 - A magnetic device using nanostructured ferrite fillers

Ferrite inductors were prepared using nanostructured and micron-scale powders as follows. One-tenth of a mole (27.3 grams) of iron chloride hexahydrate ($\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$) was dissolved in 500 ml of distilled water along with 0.025 moles (3.24 grams) of nickel chloride (NiCl_2) and 0.025 moles (3.41 grams) of zinc chloride (ZnCl_2). In another large beaker, 25 grams of NaOH was dissolved in 500 ml of distilled water. While stirring the NaOH solution rapidly, the metal chloride solution was slowly added, forming a precipitate instantaneously. After 1 minute of stirring, the precipitate solution was vacuum filtered while frequently rinsing with distilled water. After the precipitate had dried enough to cake and crack, it was transferred to a glass dish and allowed to dry for 1 hour in an 80°C drying oven. At this point, the precipitate was ground with a mortar and pestle and calcined in air at 400°C for 1 hour to remove any remaining moisture and organics.

BET analysis of the produced powder yielded a surface area of 112 m^2/g , confirming the presence of nanometer-sized individual particles with an estimated BET particle size of 11 nm. XRD analyses of all nanoscale powders showed the formation of a single $(\text{Ni}, \text{Zn})\text{Fe}_2\text{O}_4$ ferrite phase with peak shapes characteristic of nanoscale powders. XRD peak broadening calculations reported an average crystallite size of 20 nm of the thermally quenched powders and 8 nm for the chemically derived powders. SEM-EDX analyses of sintered nanopowder pellets showed an average composition of 14.8% NiO, 15.8% ZnO, and 69.4% Fe_2O_3 , which corresponded to the targeted stoichiometric composition of the $\text{Ni}_{0.5}\text{Zn}_{0.5}\text{Fe}_2\text{O}_4$.

Nanoscale ferrite filler powders were uniaxially pressed at 5000 pounds in a quarter-inch diameter die set into green pellets. The powders were mixed with 2

weight percent Duramax™ binder for improved sinterability. The amount of powder used for pressing varied from 1.5 to 1.7 grams, typically resulting in cylinders having a post-sintered height of approximately 1.5 cm. To avoid cracking and other thermal stress effects, a multi-level heating profile was employed. The pellets were fired at a rate of 5°C/min to 300°C, 10°C/min to 600°C, and 20°C/min to the final sintering temperature, where it was held for four hours. Pellets were cooled from the sintering temperature at a rate of 10°C/min to ensure the sintering temperature ranged from 900°C to 1300°C, but was typically greater than 1200°C to ensure an acceptable density. Sintered pellets were then wound with 25 turns of 36 gauge enamel coated wire, the wire ends were stripped, and the completed solenoids were used for electrical characterization. An air coil was prepared for the purpose of calculating magnetic properties. This coil was created by winding 25 turns of the enamel coated wire around the die plunger used previously. This coil was taped with masking tape, slid off the plunger slowly to maintain shape and characteristics, and was characterized along with the ferrite solenoids.

Inductance characterization was performed with a Hewlett-Packard 429A RF Impedance/Materials Analyzer. Impedance, parallel inductance, q factor, and impedance resistance were measured over a logarithmic frequency sweep starting at 1 MHz and ending at 1.8 GHz. Values for permeability (μ) and loss factor (LF) were calculated from inductance (L), air coil inductance (L_0), and impedance resistance (R) using the following equations:

$$\mu = \frac{L}{L_0} \quad (3)$$

$$LF = \frac{L_0 R}{\omega L^2} \quad (4)$$

Resistivity measurements were made with a Keithley® 2400 SourceMeter using a four-wire probe attachment and TestPoint™ data acquisition software. Voltage was ramped from 0.1 to 20 volts while simultaneously measuring current. The results were plotted as field (voltage divided by pellet thickness) versus current

density (current divided by electrode cross sectional area). The slope of this graph gives material resistivity (ρ).

Table 3 summarizes electrical properties of inductors prepared from micron-sized powder or from nanopowder. In most cases there is an advantage to using nanoscale precursor powder instead of micron-sized powder. It is important to keep in mind that all measurements were taken from cylindrical devices, which have inherently inefficient magnetic properties. Solenoids of this shape were used in this study because of the ease of production and excellent reproducibility. All measured properties would be expected to improve with the use of higher magnetic efficiency shapes such as cores or toroids, or by improving the aspect ratio (length divided by diameter) of the cylindrical samples.

Loss Factor @ 1 MHz			Critical Frequency		
	Micron	Nano		Micron	Nano
Average	0.0032	0.0025	Average	68.9	78.3 MHz
Q Factor @ 1 MHz			Resistivity		
	Micron	Nano		Micron	Nano
Average	37.2	52.2	Average	0.84	33.1 M Ω -cm

Table 3

The inductors made from ferrite nanopowders exhibited significantly higher Q-factor, critical resonance frequency, and resistivity. They also exhibited more than 20% lower loss factor as is desired in commercial applications.

Other embodiments of the invention will be apparent to those skilled in the art from a consideration of the specification or practice of the invention disclosed herein. It is intended that the specification and examples be considered as exemplary only, with the true scope and spirit of the invention being indicated by the following claims.

What is claimed is:

1. A nanostructured filler, intimately mixed with a matrix, wherein,

the nanostructured filler has a domain size sufficiently small that a desired material property of the filler varies by a size confinement effect, the desired material property differing by at least 20% from the same property of a powder having the same composition as the nanostructured filler and having a domain size of at least one micron, and

the desired material property is selected from the group consisting of refractive index, transparency to light, reflection characteristics, resistivity, permittivity, permeability, coercivity, B-H product, magnetic hysteresis, breakdown voltage, skin depth, curie temperature, dissipation factor, loss factor, work function, band gap, electromagnetic shielding effectiveness, radiation hardness, biocompatibility, chemical reactivity, and thermal conductivity.

2. A nanostructured filler, intimately mixed with a matrix, the filler and matrix together forming a nanocomposite structure, wherein,

the nanostructured filler has a domain size sufficiently small that a desired material property of the nanocomposite differs by at least 20% from the same property of a composite comprising a filler of the same composition as the nanostructured filler and having a domain size of at least one micron, intimately mixed with a matrix of the same composition as the matrix of the nanocomposite, the proportions of filler and matrix being the same for the composite and the nanocomposite, and

the desired material property is selected from the group consisting of refractive index, transparency to light, reflection characteristics, resistivity, permittivity, permeability, coercivity, B-H product, magnetic hysteresis, breakdown voltage, skin depth, curie temperature, dissipation factor, loss factor, work function, band gap, electromagnetic shielding effectiveness, radiation hardness, chemical reactivity, thermal conductivity, temperature coefficient of an electrical

property, voltage coefficient of an electrical property, thermal shock resistance, biocompatibility, and wear rate.

3. The nanostructured filler of claim 1 or 2, wherein

5 the nanostructured filler comprises at least one element selected from the
 group consisting of actinium, aluminum, arsenic, barium, beryllium,
 bismuth, cadmium, calcium, cerium, cesium, cobalt, copper,
 dysprosium, erbium, europium, gadolinium, gallium, gold, hafnium,
 hydrogen, indium, iridium, iron, lanthanum, lithium, magnesium,
10 manganese, mendelevium, mercury, molybdenum, neodymium,
 neptunium, nickel, niobium, osmium, palladium, platinum, potassium,
 praseodymium, promethium, protactinium, rhenium, rubidium,
 scandium, silver, sodium, strontium, tantalum, terbium, thallium,
 thorium, tin, titanium, tungsten, vanadium, ytterbium, yttrium, zinc,
15 and zirconium.

4. The nanostructured filler of claim 3, wherein the nanostructured filler comprises a
particle substantially composed of a material selected from the group
consisting of ferrites, dielectrics, metals, metal alloys, ceramics, and polymers.

20

5. The nanostructured filler of claim 1 or 2, wherein the nanostructured filler
comprises a particle having a coating.

25

6. The nanostructured filler of claim 5, wherein the matrix is a polymer and the
coating is substantially composed of a material selected from the group
consisting of the polymer and related monomers.

30

7. The nanostructured filler of claim 5, wherein the coating and the matrix have
substantially the same composition.

8. The nanostructured filler of claim 1 or 2, wherein the nanostructured filler has an
average domain size of less than or equal to 100 nm.

9. The nanostructured filler of claim 1 or 2, wherein the nanostructured filler has an average domain size of less than or equal to 50 nm.
10. The nanostructured filler of claim 1 or 2, wherein the nanostructured filler has an average domain size of less than or equal to 30 nm.
11. The nanostructured filler of claim 1 or 2, wherein the matrix comprises a polymer.
12. The nanostructured filler of claim 11, wherein the polymer is selected from the group consisting of poly(methyl methacrylate), poly(vinyl alcohol), polycarbonates, polyalkenes, and polyaryls.
13. The nanostructured filler of claim 1 or 2, wherein the matrix comprises a material selected from the group consisting of ceramics, ceramic blends, metals, and metal alloys.
14. The nanostructured filler of claim 1 or 2, wherein the nanostructured filler and the matrix are mixed to form a composite having a volume fraction of nanostructured filler not greater than 95%.
15. The nanostructured filler of claim 1 or 2, wherein the nanostructured filler and the matrix are mixed to form a composite having a volume fraction of nanostructured filler not greater than 80%.
16. A device comprising the nanostructured filler of claim 1 or 2.
17. The device of claim 16, where the device is selected from the group consisting of electrical devices, magnetic devices, optical devices, biomedical devices, and electrochemical devices.
18. The device of claim 16, where the device is selected from the group consisting of

varistors, inductors, batteries, medical implants, and drug delivery vehicles.

19. A method of producing a composite, comprising

blending a nanoscale filler composition with any of a matrix composition and
5 a matrix precursor composition, the filler composition comprising no
more than 95 volume percent of the composite, wherein,

the nanostructured filler has a domain size sufficiently small that a desired
material property of the nanocomposite differs by at least 20% from
the same property of a composite comprising a filler of the same
10 composition as the nanostructured filler, intimately mixed with a
matrix of the same composition as the matrix of the nanocomposite,
the proportions of filler and matrix being the same for the composite
and the nanocomposite, and

the desired material property is selected from the group consisting of
15 refractive index, transparency to light, reflection characteristics,
resistivity, permittivity, permeability, coercivity, B-H product,
magnetic hysteresis, breakdown voltage, skin depth, curie temperature,
dissipation factor, work function, band gap, electromagnetic shielding
effectiveness, radiation hardness, chemical reactivity, thermal
20 conductivity, temperature coefficient of an electrical property, voltage
coefficient of an electrical property, thermal shock resistance,
biocompatibility, and wear rate.

20. A method of producing a composite, comprising

25 blending a nanoscale filler composition with any of a matrix composition and
a matrix precursor composition, the filler composition comprising no
more than 95 volume percent of the composite, wherein,

the nanostructured filler has a domain size sufficiently small that a
desired material property of the nanocomposite differs by at
30 least 20% from the same property of a composite comprising a
filler of the same composition as the nanostructured filler,
intimately mixed with a matrix of the same composition as the

matrix of the nanocomposite, the proportions of filler and matrix being the same for the composite and the nanocomposite, and

the desired material property is selected from the group consisting of refractive index, transparency to light, reflection characteristics, resistivity, permittivity, permeability, coercivity, B-H product, magnetic hysteresis, breakdown voltage, skin depth, curie temperature, dissipation factor, work function, band gap, electromagnetic shielding effectiveness, radiation hardness, chemical reactivity, thermal conductivity, temperature coefficient of an electrical property, voltage coefficient of an electrical property, thermal shock resistance, biocompatibility, and wear rate.

21. The method of claim 19 or 20, wherein the nanostructured filler comprises at least one element selected from the group consisting of actinium, aluminum, arsenic, barium, beryllium, bismuth, cadmium, calcium, cerium, cesium, cobalt, copper, dysprosium, erbium, europium, gadolinium, gallium, gold, hafnium, hydrogen, indium, iridium, iron, lanthanum, lithium, magnesium, manganese, mendelevium, mercury, molybdenum, neodymium, neptunium, nickel, niobium, osmium, palladium, platinum, potassium, praseodymium, promethium, protactinium, rhenium, rubidium, scandium, silver, sodium, strontium, tantalum, terbium, thallium, thorium, tin, titanium, tungsten, vanadium, ytterbium, yttrium, zinc, and zirconium.

22. The method of claim 19 or 20, wherein the nanostructured filler comprises a particle having a coating.

23. The method of claim 19 or 20, wherein the matrix composition comprises a material selected from the group consisting of poly(methyl methacrylate), poly(vinyl alcohol), polycarbonate, polyalkenes, and polyaryls.

24. The method of claim 19 or 20, wherein the method further comprises curing the blended filler and matrix to form a solid composite.
- 5 25. The method of claim 19 or 20, wherein the matrix precursor composition represents a polymer precursor, and wherein the method further comprises polymerizing the precursor after blending the filler and the precursor.
- 10 26. The method of claim 19 or 20, wherein the matrix composition is dissolved in a solvent before blending with the filler, and wherein the solvent is removed after blending with the filler.
- 15 27. The method of claim 19 or 20, wherein the matrix composition is substantially in the form of a powder, and the powder is compacted to form a solid composite after blending with the filler.
28. The method of claim 19 or 20, wherein the nanostructured filler has an average domain size of less than or equal to 100 nm.
- 20 29. The method of claim 19 or 20, wherein the nanostructured filler has an average domain size of less than or equal to 50 nm.
30. The method of claim 19 or 20, wherein the nanostructured filler has an average domain size of less than or equal to 30 nm.
- 25 31. The method of claim 19 or 20, wherein the filler comprises no more than 80 volume percent of the composite.




FIG. 1




FIG. 2




FIG. 4




FIG. 3

INTERNATIONAL SEARCH REPORT

In national Application No

PCT/US 98/11959

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08K11/00 C08J3/22

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08K C08J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P.X	EP 0 810 259 A (BAYER AG ; INST NEUE MATERIALIEN GEM GMBH (DE)) 3 December 1997 see page 3, line 4 - line 7 see claims 1-13	1-31
X	--- DATABASE WPI Section Ch, Week 9618 Derwent Publications Ltd., London, GB: Class A17, AN 96-175779 XP002078193 & JP 08 053573 A (MITSUBISHI CHEM CORP) . 27 February 1996 see abstract --- -/-	1-31

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

*** Special categories of cited documents :**

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

21 September 1998

Date of mailing of the international search report

05/10/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Siemens, T

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/11959

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0810259 A	03-12-1997	DE 19621308 A	04-12-1997
EP 0004859 A	31-10-1979	DE 2817027 B	19-07-1979
		WO 7900946 A	15-11-1979
		JP 55500236 T	24-04-1980
US 4760296 A	26-07-1988	CA 1168857 A	12-06-1984
		US 4546041 A	08-10-1985
		JP 3031738 B	08-05-1991
		JP 57002361 A	07-01-1982
		NL 8004628 A, B,	01-12-1981
FR 2722492 A	19-01-1996	JP 8081207 A	26-03-1996
		US 5646078 A	08-07-1997
US 5194128 A	16-03-1993	US 5062936 A	05-11-1991

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 98/11959

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DATABASE WPI Section Ch, Week 9518 Derwent Publications Ltd., London, GB; Class A23, AN 95-137044 XP002078194 & JP 07 062232 A (TOYOCO KK), 7 March 1995 see abstract ---	1-31
X	EP 0 004 859 A (HUELS CHEMISCHE WERKE AG) 31 October 1979 see table 1 see claim 1 ---	1-31
X	US 4 760 296 A (JOHNSTON DON R ET AL) 26 July 1988 see claims 1,5 ---	1-31
X	FR 2 722 492 A (SUMITOMO CHEMICAL COMPANY LIMITED) 19 January 1996 see claims 1-6 ---	1-31
A	US 5 194 128 A (BEATY JOHN S ET AL) 16 March 1993 cited in the application see claims 1-14 -----	1-31